

>> Standard Diffractive Optical Elements (Polymer materials, Ø 8 mm)

	DOE Item #	Description	Design Wavelength	Pattern Size @ 100 mm Distance (@ Design Wavelength, Values: mm)				Pattern Angles (@ Design Wavelength)				Optimum Wavelength Range(s)
				a	b	c	d	α	β	γ	δ	
Multi Lines:												
	DE-R 213	11 Lines (Square)	635nm*	76.7	54.4	5.4	54.4	42.0	30.4	3.0	30.4	530-670 nm
	DE-R 233	7 Lines (Square)	635nm*	54.0	38.2	6.4	38.2	30.2	21.6	3.6	21.6	530-670 nm
	DE-R 250	5 Lines (Rectangular)	660nm*	55.0	10.9	2.7	53.9	30.8	6.2	1.6	30.2	590-670 nm
	DE-R 251	7 Lines (Rectangular)	650nm	15.5	9.0	1.5	12.6	8.9	5.2	0.8	7.2	590-730 nm
	DE-R 252	5 Lines (Square)	635nm*	42.7	30.2	7.5	30.2	24.1	17.2	4.3	17.2	530-670 nm
	DE-R 253	11 Lines (Square, Thin Lines)	635nm*	76.4	54.0	5.4	54.0	41.8	30.2	3.0	30.2	530-670 nm
	DE-R 254	25 Lines (Square)	660nm*	68.4	48.3	2.0	48.3	37.7	27.2	1.1	27.2	530-670 nm
	DE-R 255	65 Lines (Square, Central Line Thicker)	660nm*	45.6	32.2	0.5	32.2	25.7	18.3	0.3	18.3	530-670 nm
	DE-R 284	41 Lines (Rectangular)	660nm*	133.4	104.0	2.6	78.0	67.4	54.9	1.4	42.6	600-700 nm
Dot Matrix:												
	DE-R 206	17 x 17 Dots	660nm	38.0	26.6	1.7	26.6	21.5	15.2	0.9	15.2	590-730 nm
	DE-R 223	2 x 2 + 1 Dots	635nm	28.3	19.9	19.9	19.9	16.1	11.4	11.4	11.4	635 & 405 nm
	DE-R 231	101 x 101 Dots	660nm	12.8	9.1	0.1	9.1	7.4	5.2	0.05	5.2	635-680 nm
	DE-R 241	21 x 21 Dots	635nm	11.9	8.4	0.4	8.4	6.8	4.8	0.2	4.8	560-730 nm
	DE-R 242	16 x 16 Dots	635nm	12.4	8.8	0.6	8.8	7.1	5.0	0.3	5.0	530-730 nm
	DE-R 243	17 x 17 Dots	635nm	12.4	8.8	0.5	8.8	7.1	5.0	0.3	5.0	550-720 nm
	DE-R 244	13 x 13 Dots	635nm	7.4	5.3	0.4	5.3	4.3	3.0	0.3	3.0	590-670 nm
	DE-R 257	51 x 51 Dots	660nm*	56.9	40.3	0.8	40.3	31.8	22.8	0.5	22.8	560-720 nm
	DE-R 258	11 x 11 Dots	635nm*	71.2	50.3	5.0	50.3	39.2	28.2	2.8	28.2	590-690 nm
	DE-R 339	6 x 6 Dots	635nm	11.7	8.3	1.7	8.3	6.7	4.7	0.9	4.7	590-690 nm
Crosshair:												
	DE-R 205	Cross – 5@650	650nm	8.7				5.0				580-660 nm
	DE-R 212	Cross – 25@532	532nm	45.1				25.4				500-640 nm
	DE-R 214	Cross – 2@645	645nm	3.4				2.0				600-645 nm
	DE-R 218	Cross – 15@640	640nm	26.3				15.0				500-640 nm
	DE-R 239	Cross – 5@520	520nm	8.7				5.0				488-600 nm
	DE-R 245	Cross – 10@633	633nm	17.5				10.0				570-690 nm
	DE-R 246	Cross with high contrast area	633nm	17.5				10.0				530-670 nm
	DE-R 247	Cross – 25@645	645nm	44.3				25.0				600-800 nm
	DE-R 248	Cross – 37@645	645nm	66.8				37.0				530-550 nm
	DE-R 249	Cross – 45@633	633nm	83.0				45.0				500-640 nm
	DE-R 270	Cross – 30@640	640nm	53.6				30.0				580-650 nm
	DE-R 280	Cross – 60@635	635nm	115.5				60.0				580-690 nm
	DE-R 289	Cross – 15@520	520nm	26.4				15.0				480-550 nm
	DE-R 340	Cross – 60@450	450nm	116.1				60.3				420-520 nm
DE-R 342	Cross – 52@515	515nm	97.6				52.0				440-540 nm	
Dot Lines & Quasi-Continuous Lines:												
	DE-R 263	1 : 5 Dot Line	635nm	10.5	2.6			6.0	1.5			450-700 nm
	DE-R 264	1 : 9 Dot Line	670nm	1.6	0.2			0.9	0.1			630-780 nm
	DE-R 265	1 : 19 Dot Line	650nm	24.0	1.3			13.7	0.8			500-540 & 630-690 nm
	DE-R 266	QC - Line – 5@633	633nm	8.7	--			5.0	--			630-690 nm
	DE-R 267	QC - Line – 30@532	532nm	53.8	--			30.1	--			470-560 nm
	DE-R 281	1 : 11 Dot Line	650nm	28.9	2.9			16.5	1.6			600-730 nm
	DE-R 282	1 : 99 Dot Line	660nm	33.7	0.3			19.1	0.2			600-700 nm
	DE-R 283	QC - Line – 20@633	633nm	35.2	--			20.0	--			630-670 nm
	DE-R 286	QC - Line – 30@660	660nm	54.6	--			30.5	--			600-700 nm
	DE-R 287	QC - Line – 45@660	660nm	83.9	--			45.5	--			600-700 nm
	DE-R 337	1 : 99 Dot Line	635nm	49.3	0.5			27.7	0.3			600-700 nm
	Circles & Dot Circles:											
	DE-R 219	Solid Line Circle	592nm	55.8	--			31.2	--			480-600 nm
	DE-R 220	1 : 16 Dot Circle	515nm	81.9	16.1			44.5	9.2			480-532 nm
	DE-R 221	1 : 72 Dot Circle	532nm	36.9	1.6			20.9	0.9			400-570 nm
	DE-R 229	1 : 36 Dot Circle	532nm	6.1	0.5			3.5	0.3			480-560 nm
	DE-R 238	Solid Line Circle	520nm	6.0	--			3.4	--			520-532 nm
	DE-R 240	1 : 16 Dot Circle	635nm	18.9	3.7			10.8	2.1			530-700 nm
	DE-R 268	Solid Line Circle	488nm	77.0	--			42.1	--			488-532 nm

* Large-angle pattern that due to its symmetry properties is subject to geometrical distortion, if the DOE is used at laser wavelengths significantly different ($\Delta\lambda > 50\text{nm}$) from the design wavelength.



Special Patterns:

DOE Item #	Description	Design Wavelength	Pattern Size @ 100 mm Distance (@ Design Wavelength)	Pattern Angles (@ Design Wavelength)	Optimum Wavelength Range(s)	Image
DE-R 215	Viewfinder	645nm	Width: 26.9 mm Height: 18.0 mm Diagonal: 32.6 mm	Width: 15.3° Height: 10.3° Diagonal: 18.5°	570-750 nm	
DE-R 216	Viewfinder	488nm	Width: 9.6 mm Height: 9.6 mm Diagonal: 13.6 mm	Width: 5.5° Height: 5.5° Diagonal: 7.8°	405-488 nm	
DE-R 234	Viewfinder (Lines Square)	633nm*	Width: 60.6 mm Height: 60.6 mm Diagonal: 85.6 mm	Width: 33.7° Height: 33.7° Diagonal: 46.4°	590-730 nm	
DE-R 236	Solid Line Square	633nm*	Width: 63.1 mm Height: 63.1 mm Diagonal: 89.5 mm	Width: 35.0° Height: 35.0° Diagonal: 48.2°	530-650 nm	
DE-R 256	Square Grid 51 x 51 Lines	660nm	Width: 40.3 mm Height: 40.3 mm Diagonal: 56.9 mm Line Spacing: 0.8 mm	Width: 22.8° Height: 22.8° Diagonal: 31.8° Angle betw. Lines: 0.45°	530-660 nm	
DE-R 259	5 Rings	645nm	Width: 51.3 mm Line Spacing: 5.1 mm	Width: 28.8° Line Spacing: 2.9°	530-700 nm	
DE-R 260	Viewfinder (Circle + Cross)	645nm	Width Cross: 37.0 mm Circle Ø: 18.5 mm	Width Cross: 21.0° Circle Ø: 10.6°	570-750 nm	
DE-R 261	Viewfinder (Dot Circle + Cross)	635nm	Width Cross: 11.0 mm Circle Ø: 8.8 mm Dot Spacing: 1.1 mm	Width Cross: 6.3° Circle Ø: 5.0° Angle betw. Dots: 0.63°	570-750 nm	
DE-R 262	Viewfinder (Dot Square)	532nm	Width: 12.3 mm Height: 12.3 mm Diagonal: 17.4 mm Dot Spacing: 0.5 mm	Width: 7.0° Height: 7.0° Diagonal: 10.0° Angle betw. Dots: 0.3°	480-670 nm	
DE-R 269	10 Rings	515nm	Width: 96.2 mm Line Spacing: 4.8 mm	Width: 51.4° Line Spacing: 2.6°	488-532 nm	
DE-R 285	Hexagon	780nm	Width: 13.1 mm	Width: 7.5°	520-800 nm	
DE-R 288	Viewfinder	650nm	Width: 83.0 mm Height: 53.7 mm Diagonal: 98.9 mm	Width: 43.7° Height: 27.9° Diagonal: 52.6°	590-730 nm	
DE-R 332	33000-Dot Pseudo-Random Pattern (60° x 42° @830nm)	830nm	Width: 114.6 mm Height: 76.3 mm Diagonal: 136.9 mm	Width: 59.6° Height: 41.7° Diagonal: 68.8°	820-850 nm	
DE-R 335	33000-Dot Pseudo-Random Pattern (46° x 32° @650nm)	645nm	Width: 84.8 mm Height: 56.4 mm Diagonal: 101.3 mm	Width: 45.9° Height: 31.5° Diagonal: 53.7°	630-660 nm	

* Large-angle pattern that due to its symmetry properties is subject to geometrical distortion, if the DOE is used at laser wavelengths significantly different ($\Delta\lambda > 50\text{nm}$) from the design wavelength.